

Resistance Heating Wire Nickel-Chromium Alloy 60% Nickel / 16% Chromium - N6

$$in^2/\Omega = \frac{I^2 C_t}{p}$$

I = Current
C_t = Temperature factor
p = Surface load W/in²

Common Names: Chromel C, Nikrothal 60, N6, HAI-NiCr 60, Tophet C, Resistohm 60, Cronifer II, Electroloy, Nichrome, Alloy C, Nikrothal 6, MWS-675, Stablohm 675

Uses: Typical applications include metal-sheathed tubular elements used in hot plates, grills, toaster ovens, storage heaters, etc. and as suspended coils in air heaters used in clothes dryers, fan heaters, hand dryers, etc. In addition to its use as an electrical heating element material, it is also ideally suited for "cold" resistors, rheostats, motor overload control devices, and other types of current-temperature control equipment because of its ability to withstand high overloads. This alloy has earned a reputation as the most suitable element for domestic appliances where consistent high quality is essential but where operating temperatures do not require the high heat resisting properties of the 80/20 Nickel Chrome alloy. The alloy has good corrosion resistance except in sulfur containing atmospheres and certain controlled atmospheres. The high electrical resistivity, relatively low TCR, and its ease of fabrication have made this alloy widely used in "edge-wound" power resistors.

Composition

| Ni | Cr | Fe | Al | Si | Mn | Cu | C | Ti | Mo | W |
|-----|-----|---------|------------|------------|------------|------------|------------|------------|------------|------------|
| 60% | 16% | Balance | None/Trace | None/Trace | None/Trace | None/Trace | None/Trace | None/Trace | None/Trace | None/Trace |

Technical Data

| | | | |
|----------------------------------|-----------------------------|--|------------------|
| Resistivity (Ω/cm ²) | 675 | Resistivity (Ω/sqmf) | 530 |
| Resistivity (μΩ/cm) | 112.22 | Nom. Temp. Coeff. of Resistance (TCR) | 0.00015 |
| Std. Res. Tol. <.020" | 5% | Std. Res. Tol. >.020" | 3% |
| Thermal EMF vs. Cu | +0.002 | Specific Heat (20°C) | 0.11 cal/g |
| Density (g/cm ³) | 8.247 | Density (lb/in ³) | 0.298 |
| Thermal Conductivity | 0.132 W/cm ² /°C | Coeff. of Linear Expansion (X 10 ⁻⁶) | 14.00 0 in/in/°C |
| Approx. Melting Point | 1390°C | Max. Continuous Operating Temp. | 1100°C |
| UTS – Hard (KPSI) | 175 | YTS Tensile – Hard (KPSI) | |
| UTS – Stress Relieved (KPSI) | 155 | YTS Tensile – Stress Relieved (KPSI) | |
| UTS – Annealed (KPSI) | 95 | YTS Tensile – Annealed (KPSI) | |
| Magnetic Attraction | Faint | Emissivity – fully oxidized | 0.88 |
| Designations/Specifications | ASTM = B344-B26 | Forms Available | Wire, Ribbon |

Temperature Factor – To obtain resistance at working temperature multiply by the factor C_t, in the following table:

| °F | 68 | 212 | 392 | 572 | 752 | 932 | 1112 | 1292 | 1472 | 1652 | 1832 | 2012 | 2192 |
|-------------------|------|------|------|------|------|------|------|------|------|------|------|------|------|
| N6 C _t | 1.00 | 1.02 | 1.04 | 1.05 | 1.06 | 1.08 | 1.09 | 1.09 | 1.10 | 1.10 | 1.11 | 1.12 | 1.13 |

Alloy Data

| Gage AWG | Diameter Inch | Resistance at 68° F Ω/ft | Resistance at 68° F Ω/lb | Weight lb/1000 ft | Surface area in ² /ft | in ² /Ω at 68°F |
|----------|---------------|--------------------------|--------------------------|-------------------|----------------------------------|----------------------------|
| 000 | 0.4096 | 0.0040 | 0.0085 | 471.3005 | 15.4432 | 3839.2213 |
| 00 | 0.3648 | 0.0051 | 0.0136 | 373.7578 | 13.7525 | 2711.3252 |
| 0 | 0.3249 | 0.0064 | 0.0216 | 296.4030 | 12.2470 | 1914.7853 |
| 1 | 0.2893 | 0.0081 | 0.0343 | 235.0579 | 10.9062 | 1352.2548 |
| 2 | 0.2576 | 0.0102 | 0.0546 | 186.4091 | 9.7123 | 954.9860 |
| 3 | 0.2294 | 0.0128 | 0.0868 | 147.8289 | 8.6490 | 674.4278 |
| 4 | 0.2043 | 0.0162 | 0.1379 | 117.2335 | 7.7022 | 476.2927 |
| 5 | 0.1819 | 0.0204 | 0.2193 | 92.9703 | 6.8590 | 336.3662 |
| 6 | 0.1620 | 0.0257 | 0.3488 | 73.7287 | 6.1081 | 237.5477 |
| 7 | 0.1443 | 0.0324 | 0.5545 | 58.4694 | 5.4394 | 167.7604 |
| 8 | 0.1285 | 0.0409 | 0.8818 | 46.3683 | 4.8439 | 118.4753 |
| 9 | 0.1144 | 0.0516 | 1.4021 | 36.7717 | 4.3136 | 83.6693 |
| 10 | 0.1019 | 0.0650 | 2.2294 | 29.1612 | 3.8414 | 59.0887 |
| 11 | 0.0907 | 0.0820 | 3.5448 | 23.1259 | 3.4209 | 41.7295 |
| 12 | 0.0808 | 0.1034 | 5.6365 | 18.3396 | 3.0464 | 29.4701 |
| 13 | 0.0720 | 0.1303 | 8.9624 | 14.5440 | 2.7129 | 20.8123 |

| Gage AWG | Diameter Inch | Resistance at 68° F Ω/ft | Resistance at 68° F Ω/lb | Weight Lb/1000 ft | Surface area in ² /ft | in ² /Ω at 68°F |
|----------|---------------|--------------------------|--------------------------|-------------------|----------------------------------|----------------------------|
| 13.5 | 0.0679 | 0.1464 | 11.3014 | 12.9518 | 2.5601 | 17.4900 |
| 14 | 0.0641 | 0.1644 | 14.2509 | 11.5339 | 2.4159 | 14.6980 |
| 14.5 | 0.0605 | 0.1846 | 17.9700 | 10.2712 | 2.2798 | 12.3517 |
| 15 | 0.0571 | 0.2073 | 22.6598 | 9.1468 | 2.1514 | 10.3800 |
| 15.5 | 0.0539 | 0.2327 | 28.5736 | 8.1454 | 2.0302 | 8.7230 |
| 16 | 0.0508 | 0.2614 | 36.0307 | 7.2537 | 1.9159 | 7.3305 |
| 16.5 | 0.0480 | 0.2935 | 45.4339 | 6.4596 | 1.8080 | 6.1603 |
| 17 | 0.0453 | 0.3296 | 57.2911 | 5.7524 | 1.7061 | 5.1770 |
| 17.5 | 0.0427 | 0.3701 | 72.2429 | 5.1227 | 1.6100 | 4.3505 |
| 18 | 0.0403 | 0.4156 | 91.0968 | 4.5619 | 1.5194 | 3.6561 |
| 18.5 | 0.0380 | 0.4667 | 114.8710 | 4.0625 | 1.4338 | 3.0724 |
| 19 | 0.0359 | 0.5240 | 144.8499 | 3.6177 | 1.3530 | 2.5820 |
| 19.5 | 0.0339 | 0.5884 | 182.6526 | 3.2217 | 1.2768 | 2.1698 |
| 20 | 0.0320 | 0.6608 | 230.3211 | 2.8690 | 1.2049 | 1.8234 |
| 20.5 | 0.0302 | 0.7420 | 290.4299 | 2.5549 | 1.1370 | 1.5324 |
| 21 | 0.0285 | 0.8332 | 366.2259 | 2.2752 | 1.0730 | 1.2877 |
| 21.5 | 0.0269 | 0.9357 | 461.8030 | 2.0261 | 1.0126 | 1.0822 |
| 22 | 0.0253 | 1.0507 | 582.3236 | 1.8043 | 0.9555 | 0.9094 |
| 22.5 | 0.0239 | 1.1799 | 734.2976 | 1.6068 | 0.9017 | 0.7643 |
| 23 | 0.0226 | 1.3249 | 925.9335 | 1.4309 | 0.8509 | 0.6423 |
| 23.5 | 0.0213 | 1.4878 | 1167.5822 | 1.2742 | 0.8030 | 0.5397 |
| 24 | 0.0201 | 1.6707 | 1472.2961 | 1.1347 | 0.7578 | 0.4536 |
| 24.5 | 0.0190 | 1.8761 | 1856.5338 | 1.0105 | 0.7151 | 0.3812 |
| 25 | 0.0179 | 2.1067 | 2341.0493 | 0.8999 | 0.6748 | 0.3203 |
| 25.5 | 0.0169 | 2.3657 | 2952.0128 | 0.8014 | 0.6368 | 0.2692 |
| 26 | 0.0159 | 2.6565 | 3722.4248 | 0.7136 | 0.6009 | 0.2262 |
| 26.5 | 0.0150 | 2.9831 | 4693.8977 | 0.6355 | 0.5671 | 0.1901 |
| 27 | 0.0142 | 3.3498 | 5918.9042 | 0.5659 | 0.5351 | 0.1598 |
| 27.5 | 0.0134 | 3.7616 | 7463.6111 | 0.5040 | 0.5050 | 0.1343 |
| 28 | 0.0126 | 4.2240 | 9411.4532 | 0.4488 | 0.4766 | 0.1128 |
| 29 | 0.0113 | 5.3264 | 14964.8397 | 0.3559 | 0.4244 | 0.0797 |
| 30 | 0.0100 | 6.7164 | 23795.0952 | 0.2823 | 0.3779 | 0.0563 |
| 31 | 0.0089 | 8.4693 | 37835.7917 | 0.2238 | 0.3366 | 0.0397 |
| 32 | 0.0080 | 10.6796 | 60161.4376 | 0.1775 | 0.2997 | 0.0281 |
| 33 | 0.0071 | 13.4667 | 95660.7066 | 0.1408 | 0.2669 | 0.0198 |
| 34 | 0.0063 | 16.9813 | 152106.9169 | 0.1116 | 0.2377 | 0.0140 |
| 35 | 0.0056 | 21.4130 | 241860.1638 | 0.0885 | 0.2117 | 0.0099 |
| 36 | 0.0050 | 27.0013 | 384573.8249 | 0.0702 | 0.1885 | 0.0070 |
| 37 | 0.0045 | 34.0481 | 611498.0843 | 0.0557 | 0.1679 | 0.0049 |
| 38 | 0.0040 | 42.9339 | 972322.8230 | 0.0442 | 0.1495 | 0.0035 |
| 39 | 0.0035 | 54.1388 | 1546058.2730 | 0.0350 | 0.1331 | 0.0025 |
| 40 | 0.0031 | 68.2678 | 2458335.9836 | 0.0278 | 0.1185 | 0.0017 |
| 41 | 0.0028 | 86.0843 | 3908918.5147 | 0.0220 | 0.1056 | 0.0012 |
| 42 | 0.0025 | 108.5504 | 6215441.6878 | 0.0175 | 0.0940 | 0.0009 |
| 43 | 0.0022 | 136.8798 | 9882967.6876 | 0.0139 | 0.0837 | 0.0006 |
| 44 | 0.0020 | 172.6025 | 15714579.1432 | 0.0110 | 0.0746 | 0.0004 |
| 45 | 0.0018 | 217.6480 | 24987231.1087 | 0.0087 | 0.0664 | 0.0003 |
| 46 | 0.0016 | 274.4494 | 39731367.4639 | 0.0069 | 0.0591 | 0.0002 |
| 47 | 0.0014 | 346.0748 | 63175529.6810 | 0.0055 | 0.0526 | 0.0002 |
| 48 | 0.0012 | 436.3929 | 100453314.4774 | 0.0043 | 0.0469 | 0.0001 |
| 49 | 0.0011 | 550.2821 | 159727483.7338 | 0.0034 | 0.0418 | 0.0001 |
| 50 | 0.0010 | 693.8939 | 253977374.3919 | 0.0027 | 0.0372 | 0.0001 |

Information presentation property of Hyndman Industrial Products, Inc., 3508 Independence Drive, Fort Wayne, IN 46808-4518, 888.496.3626, www.resistancewire.com

(Disclaimer) This information is provided for information purposes only "As is." Hyndman Industrial Products, Inc. makes no warranty of any kind with respect to the subject matter or accuracy of the information. Hyndman Industrial Products, Inc. specifically disclaims all warranties, expressed, implied or otherwise, including without limitation, all warranties of merchantability and fitness for a particular purpose. This publication may include technical inaccuracies or typographical errors; changes may be made to the information herein. If errors are found, please submit the correction via e-mail to: webmaster@resistancewire.com. Include correction, and page address if possible. All trademarks referenced are the property of their respective owners. Ownership can be researched at www.uspto.gov or by contacting Hyndman Industrial Products, Inc.